

Technical Performance Specifications

Color	-	Black
Dry Film Thickness	ASTM D7091-05	0.8-1.2 mils
Gloss - 60°	ASTM D523-89	65 - 90%
Pencil Hardness	ASTM D3363-00	2 H Minimum
Water Immersion	ASTM D870-02	>1000 hours
Cross Hatch Adhesion	ASTM D3359-97	4B - 5B
Impact Resistance	ASTM D2794-93	160 in./lbs. Direct
Salt Spray	ASTM B117-97	6048+ Hours
Humidity	ASTM D2247-99	1000 Hours Minimum
Durability	-	Very Flexible, Consistent Film
Heat Transfer Reduction	ARI 410	Less Than 1%
Bridging	-	No Bridging Guaranteed
Coating Of Enhanced Fins	-	Up to 30 fins per inch
pH Range	-	3 - 12
Temperature Limits		-40° F to 400° F